### AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

- (original) A method of preparing the surface of a coated structure for the application of an overcoat, the method comprising:
   cleaning the surface of the coat with cleaning solution; and applying an oxidising agent to the surface.
- 2. (original) A method according to claim 1, wherein the cleaning comprises soaking the surface of the coat with the cleaning solution.
- (original) A method according to claim 2, wherein the soaking is for a time in the range from about 30 seconds to about 5 minutes.
- 4. (currently amended) A method according to any preceding claim Claim 1, wherein the cleaning comprises agitating the surface of the coat with the cleaning solution.
- 5. (original) A method according to claim 4, wherein the agitating is for a time in the range from about 30 seconds to about 20 minutes.
- 6. (original) A method according to claim 4, wherein the agitating is for a time in the range from about 2 minutes to about 10 minutes.

## HARRIS et al. U.S. National Phase of PCT/GB04/04873

- (currently amended) A method according to any one of claims 4 to 6 Claim
   4, wherein the agitating comprises agitating the surface with a brush.
- 8. (currently amended) A method according to any preceding claim Claim 1, wherein the cleaning comprises soaking the surface of the coat before agitating the surface with the cleaning solution.
- (currently amended) A method according to any preceding claim Claim 1,
   wherein the cleaning solution is an alkaline cleaner.
- (currently amended) A method according to any preceding claim Claim 1,
   wherein the cleaning solution is a water-based cleaner.
- (currently amended) A method according to any preceding claim Claim 1,
   wherein the oxidising agent is peroxide.
- (original) A method according to claim 11, wherein the peroxide is hydrogen peroxide.
- 13. (original) A method according to claim 12, wherein the concentration of the hydrogen peroxide is in the range from about 1% to about 10%.

## HARRIS et al. U.S. National Phase of PCT/GB04/04873

- 14. (original) A method according to claim 12, wherein the concentration of the hydrogen peroxide is 3%.
- 15. (currently amended) A method according to <u>any preceding claim Claim 1</u>, wherein the applying the oxidising agent comprises spraying the oxidising agent onto the surface of the coat.
- 16. (currently amended) A method according to any preceding claim Claim 1, wherein the coat is paint.
- 17. (currently amended) A method according to any preceding claim Claim 1, wherein the coat is a primer.
- 18. (currently amended) A method according to any preceding claim Claim 1, wherein the overcoat is paint.
- 19. (currently amended) A method according to any preceding claim Claim 1, wherein the structure is metallic.
- 20. (currently amended) A method according to any preceding claim Claim 1, wherein the structure is formed of a composite material.

# HARRIS et al. U.S. National Phase of PCT/GB04/04873

- 21. (currently amended) A method according to any preceding claim 1, wherein the structure is an aircraft or aerospace structure.
- 22. (original) A method of applying an overcoat to the surface of a coated structure, the method comprising:

preparing the surface of the coat in accordance with the method of any preceding claim; and applying the overcoat.

### Claim 23 (cancelled)

- 24. (currently amended) A coated structure wherein the structure has been treated in accordance with the method of any preceding claim Claim 1.
- 25. (original) A coated structure according to claim 24, wherein the structure is an aircraft or aerospace structure.
- 26. (original) A cleaning kit for preparing the surface of the coat of a coated structure for the application of an overcoat, the kit comprising a cleaning solution and an oxidising agent.